

# Review of Brazilian Activities Related to the Thorium Fuel Cycle and Production of Thorium Compounds at IPEN-CNEN/SP

Paulo Ernesto de Oliveira Lainetti, Antônio Alves de Freitas and Ana Copat Mindrisz

*Centro de Química e Meio Ambiente, IPEN-CNEN/SP (Instituto de Pesquisas Energéticas e Nucleares), São Paulo 2242 05508-000, Brazil*

Received: April 11, 2014 / Accepted: June 03, 2014 / Published: December 31, 2014.

**Abstract:** The Brazilian's interest in the nuclear utilization of thorium has started in the 1950s as a consequence of the abundant occurrence of monazite sands. Since the 1960s, IPEN-CNEN/SP (Instituto de Pesquisas Energéticas e Nucleares) has performed some developments related to the thorium fuel cycle. The production and purification of thorium compounds was carried out at IPEN for about 18 years and the main product was the thorium nitrate with high purity, having been produced over 170 metric tons of this material in the period, obtained through solvent extraction. The thorium nitrate was supplied to the domestic industry and used for gas portable lamps (Welsbach mantle). Although the thorium compounds produced have not been employed in the nuclear area, several studies were conducted. Therefore, those activities and the accumulated experience are of strategic importance, on one hand, due to huge Brazilian thorium reserves, on the other hand, by the resurgence of the interest of thorium for the Generation IV advanced reactors. This paper presents a review of the Brazilian research and development activities related to thorium technology.

**Key words:** Thorium, compounds, purification, processes.

## 1. Introduction

The utilization of the thorium fuel cycle has been considered attractive since the Post-World War II period, owing to the excellent neutron characteristics of uranium-233 and the availability of vast thorium resources. Starting around the end of the 1950s, a great number of prototypes based on thorium were built. Nevertheless, the great success of the LWR (light water reactors), the good availability of uranium and the reliability in the  $UO_2$  fuels, lead to abandon the interest devoted to thorium cycle in some extent. Thorium is three to four times more abundant than uranium in the earth's crust and, although not fissile, all thorium can be used to produce U-233, from the absorption of neutrons and subsequent radioactive

decay. This uranium isotope is an excellent fuel for use in practically all nuclear reactors types. Before the advent of atomic energy and the appearance of thorium as a source producing secondary fuel (uranium-233), its main application was in the incandescent mantles manufacture. Globally, the 80 and 90 decades were characterized by a significant reduction in the nuclear power growth rate. However, from the year 2000, there was a significant change in the international arena, with the "renaissance" of interest in nuclear power, even in countries that had abandoned nuclear power. In this context, it becomes important to use thorium as nuclear fuel of the advanced Generation IV reactors, with start-up scheduled for 2030. Unfortunately, contrary to what is happening in most developed countries in recent years, Brazil is paying little attention to thorium, even less than that in the past, despite its large reserves. Brazil has one of the biggest world nuclear resources

---

**Corresponding author:** Paulo Ernesto de Oliveira Lainetti, professor, research fields: thorium processing and environment. E-mail: lainetti@ipen.br.

(uranium and thorium), being the sixth natural uranium resource in the world, one of the biggest worldwide thorium resources and only one third of its territorial area has been prospected until now. It is possible that thorium constitutes the major Brazilian energy reserve, supplanting much oil (despite the findings of the pre-salt) and uranium. However, the lack of incentives prevented a greater knowledge of the mineral occurrences and their dimensions in Brazilian territory.

## **2. Historical Background of the Brazilian Interest in Thorium**

The Brazilian's interest in the nuclear utilization of thorium has started in the 1950s as a consequence of the abundant occurrence of monazite sands. Brazil has uranium resources of 309,000 t  $U_3O_8$ , besides one of the first world thorium natural resource. The reasonably assured reserves and the estimated additional resources can reach more than 1.2 million metric tons of  $ThO_2$ , as presented in Table 1 [1]. Nevertheless, as the worldwide fuel industry and the reactor technology have been developed predominantly in the uranium field, the lack of interest in the thorium affected the prospecting and the reserve's evaluation, as well as the research and development on this matter in the country.

Brazilian systematic investigations on the use of thorium fuel cycles in nuclear power reactors started in 1965. During the 1960s and early 1970s, the work mainly concentrated on the thorium utilization in HWRs (heavy water reactors). This work was performed in the framework of a cooperation agreement with the French CEA (Commissariat à l'Énergie Atomique), by the so-called "Thorium Group". It was motivated by the results of a long term study of fuel requirements, one of the tasks of the study's committee for the first Brazilian power reactor, created by the Presidency of the Republic in 1965 and coordinated by the Brazilian CNEN (National Nuclear Energy Commission). This project was ambitious and aimed at the development of an indigenous thorium fuelled pressurized heavy water reactor concept with

prestressed concrete reactor vessel. In the frame of the international nuclear fuel cycle program, Brazil started an R & D (research and development) program on the thorium utilization in PWRs (pressurized water reactors) in 1979, within the scope of a Brazil-Germany cooperation agreement. This program lasted for almost ten years. The activities of both programs were performed at the CDTN (Nuclear Technology Development Center) in Belo Horizonte city, State of Minas Gerais [2, 3].

In the 1960s and 1970s, also started in Sao Paulo and Minas Gerais, continuing through the following decades, theoretical and experimental studies with a view not only to the use of thorium reactors, but also to the physical and chemical processes for extraction, purification of compounds, manufacturing and deployment of fuel methods of characterization, recognizing the strategic importance that this element would have for Brazil. However, there was never a national program lasting for a period sufficient to produce practical results of effective use of thorium in the Brazilian reactors. What is worse, the specific research activities on different topics of the thorium cycle have declined over time, due to the lack of interest and support. An autonomous nuclear program was carried out in the country in the 1980s. However, major political changes occurred in the program in the early 1990s. These changes contributed to the further reduction of interest in alternative nuclear fuel cycles.

## **3. Thorium Related Activities at IPEN-CNEN/SP (Instituto de Pesquisas Energéticas e Nucleares)**

Since the 1960s, IPEN has performed some activities and developments related to the thorium fuel cycle, mainly related to neutronic of thorium in nuclear reactors [4-10], thorium compounds chemistry and purification process [11-33], metallic thorium and thorium powder metallurgy [34-44], physical-chemical characterization of thorium compounds [45-59] and radiological protection [60-63].

**Table 1 Thorium potential resources in Brazil [1].**

Occurrence	Associated mineral	Average content (%)	Measured (t ThO <sub>2</sub> )	Estimated (t ThO <sub>2</sub> )
Coastal deposits	Monazite	5	2,250	-
Morro do Ferro (State of Minas Gerais)	Thorite and others	1 to 2	35,000	-
Barreiro, Araxa (State of Minas Gerais)	Pyrochlore	0.09	-	1,200,000
Area Zero, Araxa (State of Minas Gerais)	Pyrochlore	0.09	30,000	-
Alluvial and pegmatite	Monazite	5	3,000	2,500
Total	-	-	73,500 <sup>a</sup>	1,202,500

<sup>a</sup> Including 3,500 t of monazite sand of INB (Brazilian nuclear industries).

Note: The IAEA (International Atomic Energy Agency) gives (1992) 606,000 t as indicated reserves and 700,000 t of inferred reserves.

### 3.1 Thorium Chemistry and Processing of Monazite Sands in Brazil

Brazil has a long tradition of thorium technology, from mining of monazite to obtaining thorium with purity suitable for nuclear use. The first reports on the exploitation of monazite in Brazil date back to 1886, when Englishman John Gordon began exporting to the ore mined in the municipality of Prado, Bahia State in Europe, for use in lighting (incandescent gas lamps), before the advent electricity from the 1920s, when there was a decline in the consumption of monazite [1]. Interest in monazite resurfaced during World War II, due to its content of thorium. A typical Brazilian monazite contains 39% of cerium oxide, 5% of yttrium, 6% of thorium oxide and 0.3% of U<sub>3</sub>O<sub>8</sub>. In Brazil, monazite occurs mainly on the beaches of the States of Bahia, Espirito Santo and Rio de Janeiro [14]. In the late of 19th and early of 20th century, the interest in monazite increased owing to the use of thorium nitrate by gas mantle industries. Later, the use of lanthanide elements turned monazite into a much more important commodity than it was in pre-war years [64, 65].

In the 1940s, the processing of monazite sand was started in Brazil, with a view to exports of rare earths, uranium and thorium, with the work of Brill, Krumholz and colleagues [11]. Orquima-Indústrias Químicas Reunidas Company started processing of monazite in Sao Paulo aiming at taking advantage of the rare earths produced, sodium diuranate and rare earth basic carbonate, purchased by the Federal Government and

rare earth chlorides for export. In 1951, the Brazilian government banned the export of concentrates of monazite. DNPM (National Department of Mineral Production) data [66] estimate that from 1886 to 1950, were exported from Brazil about 95,000 t of monazite concentrate. In 1949, the chemical processing of monazite, to produce lanthanide chlorides and tri-sodium phosphate, was started at the Santo Amaro mill (USAM (Usina Santo Amaro)-Orquima S/A), located in Sao Paulo, the largest Brazilian city. The first phase of the monazite processing consists of the extraction, washing and drying of monazite bearing sands taken from beaches. Then, physical separation processes separate the four minerals: ilmenite, rutile, monazite and zircon. Owing to public pressure, economic and radiological problems, the chemical processing of monazite stopped in 1992 [64].

In 1960, the CNEN (Brazilian Nuclear Energy Commission) acquired the mining rights from the private companies that were exploiting the monazite in the country (SULBA (Sociedade Comercial de Minérios) and ORQUIMA (Indústrias Químicas Reunidas Companies)). Nowadays, the monazite mining is performed by the INB (Brazilian nuclear industries). Nowadays, the most important source of thorium in Brazil is the concentrated obtained in the second cake (Torta II or Cake II) of the soda opening process of the monazite, for obtaining of rare earth salts. The Torta II is an impure hydroxide containing 20% of thorium, 1% of uranium and 6.5% of rare earths. The amount of Torta II stored by INB can reach more than

3,000 t of Th content.

### 3.2 Thorium Compounds Purification at IPEN-CNEN/SP

The production and purification of thorium compounds was carried out at IPEN for about 18 years. The raw materials used were some thorium concentrates obtained from the industrialization of monazite sands, a process carried out in Sao Paulo between 1948 and 1994 on an industrial scale by the company ORQUIMA, later NUCLEMON (Nuclebrás Monazita). In the course of the industrial treatment of monazite sands in Sao Paulo, several concentrates containing thorium and rare earth elements were produced during the period 1985-2003, the main product sold was the thorium nitrate with high purity (mantle grade), having been produced over 170 metric tons of this material in the period, obtained through solvent extraction [14, 23]. The thorium nitrate was supplied to the domestic industry and particularly used for gas portable lamps (Welsbach mantle). Although the thorium compounds produced have not been employed in the nuclear area, several studies were conducted with a view to conversion of nitrate to

nuclear-grade thorium oxide suitable for the manufacture of fuel pellets, manufacture of mixed oxide pellets (U, Th) $O_2$ , obtaining of thorium tetrafluoride and its reduction to metallic thorium. The main raw material employed during the thorium nitrate production period was the thorium sulfate produced in ORQUIMA. The crystallized thorium sulfate was first transformed in thorium oxocarbonate by addition of water, sodium carbonate and sodium hydroxide. Further, the oxocarbonate was transformed in thorium nitrate by dissolution with nitric acid. To obtain high purity thorium nitrate, the most satisfactory process is purification by solvent extraction. During the period of production, it was employed the solvent extraction in pulsed columns as shown in Fig. 1.

Different alternative methods were also studied. A thorium nitrate solution is submitted to an extraction using TBP (tributyl phosphate) diluted in varsol. Thorium nitrate dissolves in tributyl phosphate to form  $Th(NO_3)_4 \cdot 2TBP$ . It is, therefore, extracted from aqueous solution as unionized compound water-free. The solubility of thorium nitrate in TBP is explored to purify the salt in a continuous counter-current



Fig. 1 Pilot plant for thorium nitrate purification using pulsed columns.

mixer-settler unit. At the end of the process, it is obtained a thorium nitrate with purity higher than 99.6%, besides a rich concentrate of rare earths, which will be purified later [26]. Having in mind an eventual substitution of the normally used thorium sulfate as the raw material for the production of pure thorium nitrate, the use of a HTBR (thorium brute concentrate) was also investigated. In the experiments using the HTBR for the separation of thorium from the rare earth elements, some alternative processes were performed: fractional hydroxides precipitation, ion exchange chromatography and precipitation with hydrogen peroxide. The experimental investigations allowed concluding that it is possible to separate thorium from the great majority of the rare earth elements using those techniques [20, 22, 24, 27, 28]. Some experiments were carried out at laboratory scale to evaluate the thorium oxide pellets dissolution and partial denitration of the thorium nitrate solutions obtained. The study corresponded to the head-end operations of the Acid THOREX ( $^{233}\text{U}$ -Th extraction) process and the best conditions of thorium oxide pellets dissolution were determined [15, 16]. Nevertheless, radical changes of the Brazilian nuclear policy, in the beginning of 1990s, determined the interruption of most R & D fuel cycle activities and the facilities shutdown in the IPEN. It was decided to suspend the thorium nitrate production in 2002 and 2003, and the pilot plant was partly decommissioned in 2003 and 2004 [66, 67].

### 3.3 Thorium Metallurgy and Thoria-Urania Mixed Oxide Preparation

In the 1960s, several developments were performed in the laboratory of the Division of Nuclear Metallurgy, Institute of Atomic Energy, regarding the production of metallic thorium and processing by powder metallurgy of the thorium sponge obtained. The studies encompassed the production of thorium achieved by reduction of thorium oxide by calcium, in special reduction bombs, in the presence of calcium chloride and iodine and processing by powder

metallurgy of the thorium obtained [34-37]. Some evaluations of different ways of obtaining  $(\text{Th-U})\text{O}_2$  mixed oxides were accomplished. Co-precipitation, mechanical mixing of uranium and thorium oxide powders and the sol-gel technique were studied in order to get knowledge of the different processes performance [25, 39-41].

## 4. Conclusion

The thorium fuel cycle presents some advantages, such as: good characteristics of the U-233, from a neutronic point of view; the thermal stability of  $\text{ThO}_2$  (melting point around 3,200-3,300 °C) that permits high burn-ups and high temperatures; the ecological argument of much lower quantity of long-lived actinides generated from fission with the thorium cycle, resulting much less long-lived wastes; the average abundance of thorium in the earth's crust that has been estimated three times as great as uranium. Since the beginning of nuclear energy development in Brazil in the 1950s, it was recognized the strategic importance of the thorium utilization for the country. Brazil has a long tradition in the thorium technology, from mining of monazite to the obtainment of thorium with purity suitable for nuclear use. The processing of monazite sand was started in Brazil in the end of 1940s, and IPEN-CNEN/SP produced more than 170 t of thorium nitrate of high purity. The accumulated experience is of strategic importance for the country, on one hand, due to huge Brazilian reserves of thorium, on the other hand, by the resurgence of the interest in the use of thorium in nuclear reactors, particularly for the advanced Generation IV reactors. Nevertheless, the lack of a Brazilian Thorium Program and the quick aging/retirements of the personnel involved are important factors determining the loss of the acquired knowledge.

## References

- [1] Gentile, E. and Filho, P. M. F. 1996. *Radioactive Minerals "Diagnosis Project" of the Brazilian Association of Metallurgy and Materials*. A material report, São Paulo.

- [2] Pinheiros, R. D. 2003. "Brazilian Experience on Thorium Fuel Cycle Investigation." *Thorium Fuel Utilization: Options and Trends* 33 (49): 13-23.
- [3] IAEA. 2005. *Thorium Fuel Cycle—Potential Benefits and Challenges*. IAEA report.
- [4] Faya, A. J. G. 1975. "Avaliação Neutrônica de Blankets de Tório Metálico em Reatores Rápidos Refrigerados por Gás." M.Sc thesis, Universidade de São Paulo.
- [5] Faya, S. C. S. 1975. "Estudo do Comportamento Térmico e Mecânico do Envoltório de Tório Metálico em Reatores Rápidos Refrigerados por Gás." M.Sc thesis, Universidade de São Paulo.
- [6] Correa, F. 1976. "Utilização de Tório em Reatores Tipo PWR." M.Sc thesis, Universidade de São Paulo.
- [7] Kosaka, N. 1976. "Estudo da Viabilidade Neutrônica de um Conjunto Subcrítico de Tório." M.Sc thesis, Universidade de São Paulo.
- [8] Sabundjian, G., and Ishiguro, Y. 1991. "Análise Básica e Comparação das Características do GCFR e LMFBR com o Ciclo do Tório pela Teoria de Difusão em um Grupo de Energia." M.Sc thesis, Universidade de São Paulo.
- [9] Moreira, J. M. L., Abe, A. Y., Figueiredo, P. M., and Lainetti, P. E. O. 1999. "Uma Proposta de Estudo Brasileira Visando a Utilização de Tório em Reatores." Presented at the 7th CGEN Congresso Geral de Energia Nuclear, Belo Horizonte, Brazil.
- [10] Maiorino, J. R., and Carluccio, T. 2004. "A Review of Thorium Utilization as an Option for Advanced Fuel Cycle-Potential Option for Brazil in the Future." Presented at 2004 ANES Americas Nuclear Energy Symposium, Miami Beach, USA.
- [11] Brill, K. J., and Krumholz, P. 1965. *Produção de Óxidos de Tório Nuclearmente Puros*. A report by Atomic Energy Institute.
- [12] Tomida, E. K., and Abrão, A. 1970. *Determinação Radiométrica de Tório em Monazitas do Brasil*. A report by Atomic Energy Institute.
- [13] Tomida, E. K. 1975. "Comportamento Cromatográfico dos Carbonatocomplexos de Lantanídeos e de Tório em Alumina. Comparação com Resinas de Troca Iônica." Ph.D. thesis, Universidade de São Paulo.
- [14] Ikuta, A. 1976. "Tecnologia de Purificação de Concentrados de Tório e sua Transformação em Produtos de Pureza Nuclear. Estudo do Sistema  $\text{Th}(\text{NO}_3)_4\text{-HNO}_3\text{-TBP-Varsol}$ ." M.Sc thesis, Universidade de São Paulo.
- [15] Forbicini, S. 1980. "Dissolução de Pastilhas de Dióxido de Tório e Ajuste de Alimentação por Desnitração. Aplicação à Separação U-Th por Extração com TBP." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [16] Camilo, R. L. 1982. "Dados de Equilíbrio no Sistema  $\text{Th}(\text{NO}_3)_4\text{-UO}_2(\text{NO}_3)_2\text{-TBP/Varsol-HNO}_3\text{-H}_2\text{O}$ . Otimização das Variáveis para a Separação de Th-232-U-233." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [17] Filho, D. B., Hespanhol, E. C. B., Baba, S., Miranda, L. E. T., and Araújo, J. A. 1989. "Reaproveitamento do Tório Contido em Resíduos Provenientes da Usina de Purificação do Tório." Accessed March 20, 2014. <http://www.ipen.br/biblioteca/ipen/1992/04368.pdf>.
- [18] Pereira, W. 1991. "Transformação de Sulfato de Tório em Nitrato de Tório por Troca Iônica." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [19] Martins, E. A. J. 1990. "Reaproveitamento de Valores nos Efluentes Líquidos das Unidades-Piloto de Urânio e Tório." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [20] Pereira, W. 1991. "Transformação de Sulfato de Tório em Nitrato de Tório por Resina de Troca Iônica." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [21] Ayoub, J. M. S. 1999. "Estudo de Diferentes Rotas de Preparação de Óxidos Binários de Tório e Urânio." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [22] Vasconcellos, M. E. 2000. "Resolução da Mistura Tório e Terras Raras por Precipitação Fracionada e Tecnologia de Troca Iônica." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [23] Lainetti, P. E. O., Abrão, A., Freitas, A. A., Carvalho, F. M., Bergamaschi, V., Cunha, E. F., and Ayoub, M. S. J. 2000. "Histórico e Perspectivas da Produção e Purificação de Compostos de Tório no IPEN." Accessed March 18, 2014. <http://www.ipen.br/biblioteca/2000/cgen/07195>.
- [24] Vasconcellos, M. E., and Abrão, A. 2000. "Resolução da Mistura Tório e Terras Raras por Tecnologia de Troca Iônica." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [25] Ayoub, J. M. S., Araujo, B. F., and Aquino, A. R. 2000. "Estudo de Diferentes Rotas de Preparação de Óxidos Binários de Tório e Urânio." Accessed March 16, 2014. <http://www.ipen.br/biblioteca/2000/cgen/07493>.
- [26] Gomes, L. F., Carvalho, F. M., Mindrisz, A. C., Scapin, M. A., Salvador, V. L. R., and Lainetti, P. E. O. 2002. "Uso de um Misturador-Decantador na Purificação de Tório Proveniente do Hidróxido de Tório Bruto." *Rev. Bras. Pesqui. Desenvol.* 4 (2): 353-6.
- [27] Freitas, A. A., Carvalho, F. M. S., Ferreira, J. C., and Abrão, A. 2002. "Transformação via Peróxido de um Hidróxido Bruto de Tório em Nitrato para Camisas de Lampião." *Rev. Bras. Pesqui. Desenvol.* 4 (3): 1606-9.
- [28] Vasconcellos, M. E., Queiroz, C. A. S., and Abrão, A. 2002. "Recuperação de Tório como Nitrato 'Mantle Grade' Usando-se um Hidróxido de Tório Bruto." *Rev. Bras. Pesqui. Desenvol.* 4 (3): 1625-8.
- [29] Zini, J., Abrão, A., Carvalho, F. M. S., Freitas, A. A., and

- Scapin, M. A. 2005. "Estudo do Tratamento de um Resíduo de Tório e Terras Raras por Cromatografia de Extração." Accessed March 14, 2014. <http://www.ipen.br/biblioteca/2005/inac/10778.pdf>.
- [30] Seneda, J. A. 2006. "Separação e Recuperação de Chumbo-208 dos Resíduos de Tório e Terras Raras Gerados na Unidade Piloto de Purificação de Nitrato de Tório." Ph.D. thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [31] Freitas, A. A. 2008. "Recuperação de Tório e Terras Raras via Peróxido do Resíduo Originado na Unidade de Purificação de Tório." M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [32] Ferreira, J. C., Freitas, A. A., Seneda, J. A., Carvalho, F. M. S., and Abrão, A. 2008. "Recuperação de Chumbo-208 Radiogênico de Resíduo Contendo Tório e Terras Raras." Presented at the Congresso Brasileiro de Engenharia e Ciência dos Materiais, Porto de Galinhas, Brazil.
- [33] Zini, J. 2010. "Usos das Cromatografias de Extração e de Troca Iônica na Separação de Tório e Terras Raras de Resíduos Industriais Gerados na Unidade de Purificação de Tório do IPEN. Aplicação das Terras Raras como Catalisadores na Geração de Hidrogênio." Ph.D. thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [34] Haydt, H. M. 1963. *Estado Atual de Tecnologia da Produção de Tório Metálico*. A report by Atomic Energy Institute.
- [35] Freitas, C. T., Haydt, H. M., and Santos, T. D. S. 1964. *Nota Preliminar Sobre a Fabricação de Pastilhas de Berílio, de Tórcia e de Soluções Sólidas de Tórcia-Urânio*. A report by Atomic Energy Institute.
- [36] Santos, T. D. S., Haydt, H. M., and Freitas, C. T. 1965. *Produção Experimental de Urânio e Tórcia Metálicos no Instituto de Energia Atômica*. A report by Atomic Energy Institute.
- [37] Capocchi, J. D. T. 1970. "Estudo Experimental da Obtenção de Tórcia Metálica por Redução Direta de Óxido de Tórcia por Metais Líquidos." M.Sc thesis, Escola Politécnica.
- [38] AmbrozioFho, F., and Vieira, R. R. 1978. "Estruturas de Solidificação de Ligas Alumínio-Tórcia." *Metalurgia* 34 (251): 691-8.
- [39] Lainetti, P. E. O., and Riella, H. G. 1991. "Preparation of Ceramic Grade UO<sub>2</sub> Powder by Atomization from Uranyl Nitrate Solutions." *Journal of Nuclear Materials* 178: 135-42.
- [40] Lainetti, P. E. O., and Riella, H. G. 1992. "Fabricação de Pós de Elevada Atividade Cerâmica por Meio de atomização de Soluções de Nitrato de Urânio." In *Proceedings of IV Congresso Geral de Energia Nuclear*, 227-30.
- [41] Nakamura, A. T. O., Gomes, R. P., Santos, G. R. T., and Lainetti, P. E. O. 1994. "Desenvolvimento do Processamento de Óxidos Mistos Utilizando-se Microesferas Obtidas via SOL-GEL." In *Proceedings of the 5th CGEN Congresso Geral de Energia Nuclear*, 559-60.
- [42] Neto, A. F., Freitas, C. T., and Lainetti, P. E. O. 1995. "Sinterização de Óxido de Urânio em Forno de Microondas e Efeito da Variação da Densidade." In *Proceedings of the 39th Congress Brasileiro de Cerâmica*, 794-9.
- [43] Neto, A. F., Freitas, C. T., and Lainetti, P. E. O. 1995. "Aplicação da Irradiação por Microondas no Processamento de Combustíveis Nucleares." In *Proceedings of the 3rd ENFIR/ENAN Encontro Nacional de Física de Reatores e Termohidráulica*, 494-9.
- [44] Filho, A. A. 2005. "Elaboração e Estudos de Recristalização de Ligas Alumínio-Magnésio-Tórcia e Alumínio-Magnésio-Nióbio." Ph.D. thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [45] Pecequilo, B. R. S. 1977. "Nova Técnica para a Determinação de Impurezas em Compostos de Urânio e de Tórcia pela Análise dos Raios Gama de Captura." Ph.D. thesis, Instituto de Energia Atômica.
- [46] Ivone, M. S. 1978. "Determinação de Urânio e Tórcia por Fluorescência de Raios-X em Minérios e Derivados." M.Sc thesis, Instituto de Energia Atômica.
- [47] Tomida, R. M. 1978. "Determinação de Iodo-131 e Tórcia em Urina." M.Sc thesis, Instituto de Energia Atômica.
- [48] Lordello, A. R. 1977. "Carreadores Espectroquímicos e o Efeito Matriz. Contribuição ao Estudo da Análise Espectrográfica de Impurezas Gerais ao Nível de Traços em Compostos de Tórcia Nuclearmente Puros." Ph.D. thesis, Instituto de Energia Atômica.
- [49] Wirkner, F. M. 1978. "Determinação do Conteúdo Total de Nitrato em Soluções de Tórcia por meio de Eletrodo Seletivo. Aplicação na Unidade Piloto de Purificação de Tórcia." M.Sc thesis, Universidade de São Paulo.
- [50] Munita, C. J. A. S. 1983. "Estudo da Troca Isotópica Associada à Troca Iônica para a Separação Radioquímica de <sup>233</sup>Th. Aplicação da Técnica na Determinação de Tórcia por Análise por Ativação." Ph.D. thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [51] Lima, M. F., and Mazzilli, B. P. 1990. "Determinação do Coeficiente de Distribuição do Tórcia no Sedimento do Rio Pinheiros." In *Proceedings of the 3rd Congresso Geral de Energia Nuclear*, 69-78.
- [52] Santos, A. J. G., and Mazzilli, B. P. 1990. "Determinação Quantitativa de Tórcia no Programa de Monitoração Ambiental do IPEN-CNEN/SP." In *Proceedings of the 3rd Congresso Geral de Energia Nuclear*, 79-88.
- [53] Vasconcellos, M. B., and Figueiredo, A. M. 1990. "Análise por Ativação Neutrônica em Amostras

- Geológicas Contendo Terras Raras, Urânio e Tório.” Esc. V. J. A. Swieca—4a. Sessão de Física Nuclear Exposition, February, São Paulo.
- [54] Kakazu, M. H., Sarkis, J. E. S., Figueiredo, A. M. G., and Armelin, M. J. A. 1992. “Determinação de Urânio e Tório em Amostras Geológicas pelas Técnicas de Espectrometria de Massa e Análise por Ativação com Nêutrons.” In *Proceedings of the 4th CGEN Congresso Geral de Energia Nuclear*, 227-30.
- [55] Camargo, I. M. C. 1994. “Determinação da Concentração dos Isótopos Naturais de Urânio e Tório em Amostras de Água.” M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [56] Silva, C. M., and Pires, M. A. F. 1994. “Determinação de Sulfato em Sais de Tório pela Técnica Gravimétrica com Separação Prévia do Tório.” In *Proceedings of the 5th CGEN Congresso Geral de Energia Nuclear*, 559-60.
- [57] Maihara, V. A., and Vasconcellos, M. B. A. 1999. “Determinação dos Níveis de Ingestão Dietética dos Elementos Arsênio, Antimônio, Cádmio, Tório, Tungstênio e Urânio em Dietas de Crianças pelo Método da Porção em Duplicata.” Presented at the 7th CGEN Congresso Geral de Energia Nuclear, Brazil.
- [58] Yamaura, M., and Matsuda, H. T. 1991. “Determinação de Tório em Soluções Simuladas do Processo ThorexporEspectrometria de Fluorescência de Raios-x.” Accessed March 14, 2014. <http://www.ipen.br/biblioteca/ipen/1991/03970.pdf>.
- [59] Gaburo, J. C. G. 1989. “Desenvolvimento de um Método de Bioanálise in Vitro para a Determinação de Tório Natural Incorporado.” M.Sc thesis, Instituto de Pesquisas Energéticas e Nucleares.
- [60] Gaburo, J. C. G., and Sordi, G. M. A. A. 1991. “Estudo Comparativo entre Servidores não Expostos e Expostos ao Tório por Meio de Análise Radiotoxicológica.” In *Proceedings of the 1st En. Nac. Aplicações Nucleares*, 179-86.
- [61] Endo, L. S., Dellamano, J. C., Marumo, J. T., and Vicente, R. 1994. “Tratamento de Cinzas de Incêndio Contaminadas com Tório-232.” In *Proceedings of the 5th CGEN Congresso Geral de Energia Nuclear*, 311-4.
- [62] Almeida, C. C., Kamonseki, M., Monteiro, E. C., Silva, T. M., Vasques, F. M. F., and Rodrigues, D. L. 2002. “Transporte de Nitrato de Tório para Firms Externas ao IPEN-CNEN/SP.” Accessed March 12, 2014. <http://www.ipen.br/biblioteca/2002/inac/08720.pdf>.
- [63] Lauria, D. C., and Rochedo, E. R. R. 2005. “The Legacy of Monazite Processing in Brazil.” *Radiation Protection Dosimetry* 114 (4): 546-50.
- [64] Paschoa, A. S. 1998. “Potential Environmental and Regulatory Implications of NORM (Naturally Occurring Radioactive Materials).” *Applied Radiation Isotopes* 49 (3): 189-96.
- [65] Maciel, A. C., and Cruz, P. R. 1973. *Perfil Analítico do Tório e Terras-Raras*. A report by DNPM (National Department of Mineral Production).
- [66] Lainetti, P. E. O. 2007. “Decommissioning of Nuclear Fuel Cycle Facilities in the IPEN-CNEN/SP.” Presented at European Nuclear Conference 2007, Brussels, Belgium.
- [67] Lainetti, P. E. O. 2005. “Decommissioning of Nuclear Fuel Cycle Facilities—IPEN’s Experience.” Presented at the 7th Enan Meeting on Nuclear Applications, Sao Paulo, Brazil.