2026 International Nuclear Atlantic Conference – INAC 2026
Escola de Guerra Naval, Rio de Janeiro, RJ, August 24 - 28, 2026

ISBN: 978-65-272-2398-6

MICROSTRUCTURAL EVOLUTION AND MECHANICAL PROPERTIES OF CuCrZr ALLOY FOR FUSION REACTORS: A CRITICAL REVIEW

dos Santos, T. F. [1]; Moraes, N. W. S. [2];
Mucsi, C. S. [3]; Rossi, J. L. [4]; Costa, I.[5]
Martinez, L. G. [6]

[1]*thiagofsantos@ipen.br,*
[2]*nathanaelmorais@gmail.com,*
[3]*csmucsi@ipen.br,*
[4]*jelrossi@ipen.br,*
[5]*icosta@ipen.br*
[6]*lgallego@ipen.br,*

1. Introduction

Copper-chromium-zirconium (CuCrZr) ternary alloys are the reference materials for plasma-facing components in fusion reactors, particularly in the International Thermonuclear Experimental Reactor (ITER) project, due to their unique combination of high thermal conductivity (>70% IACS) and superior mechanical strength achieved through precipitation hardening [1, 2]. Over the past three decades, extensive research has been conducted to understand precipitation kinetics, optimize thermomechanical processing routes, and evaluate the alloy's performance under simulated fusion conditions. However, the existing literature on CuCrZr alloys is highly fragmented, with studies employing a wide variety of compositions, processing parameters, and characterization techniques. This heterogeneity complicates the identification of optimal processing conditions and obscures the fundamental mechanisms governing the alloy's behavior. Furthermore, recent advances in characterization techniques and emerging insights into the synergistic effects of Cr and Zr additions have not yet been comprehensively reviewed.

To address these gaps, this work presents a critical review of the microstructural evolution and mechanical properties of CuCrZr alloys, focusing on: (i) the precipitation kinetics of Cr-rich phases and Cu-Zr intermetallics; (ii) the influence of thermomechanical processing routes on final properties; and (iii) performance under simulated irradiation and thermal aging conditions. This review aims to consolidate current knowledge, identify inconsistencies in the literature, and highlight critical knowledge gaps that must be addressed to qualify CuCrZr alloys for future demonstration reactors (DEMO).

2. Methodology

This review was conducted using a systematic approach to ensure comprehensiveness and reproducibility. A literature search was performed across the ScienceDirect, Web of Science, and ResearchGate databases, spanning the period from 1990 to 2026. The search strategy employed combinations of keywords, including "CuCrZr", "copper-chromium-zirconium", "fusion reactor", "precipitation hardening", "thermomechanical processing", and "irradiation damage".

The inclusion criteria were defined as follows: (i) peer-reviewed articles published in English; (ii) studies investigating CuCrZr alloys with a chromium (Cr) content between 0.4–1.5 wt% and a zirconium (Zr) content between 0.03–0.25 wt% (consistent with ITER-grade compositions); and (iii) experimental investigations focusing on microstructure, mechanical properties, or irradiation effects.

Conversely, review articles, conference abstracts lacking full-text papers, and studies on alloys with significantly divergent compositions were excluded. Initially, 100 articles were identified. Following the removal of duplicates and the rigorous application of the inclusion and exclusion criteria, 20 articles were retained for detailed analysis. These selected studies were subsequently categorized into three primary thematic areas: (1) precipitation kinetics and phase evolution; (2) thermomechanical processing and property optimization; and (3) irradiation effects and thermal stability.

3. Results and Discussion

3.1 Precipitation Kinetics and Phase Evolution

The precipitation sequence in CuCrZr alloys has been extensively studied; however, certain aspects remain subject to ongoing debate. The general consensus indicates that aging a supersaturated solid solution induces the sequential precipitation of Cr-rich phases, followed by the formation of Cu-Zr intermetallics [3, 4]. Nevertheless, the exact crystallographic nature of these precipitates and their coherency with the copper matrix exhibit significant variation depending on the aging temperature and duration. Table I summarizes the primary findings from the literature regarding the precipitation sequence in CuCrZr alloys. It is evident that while Cr precipitation is well-documented, the specific role of Zr remains less definitively understood. Some studies report the formation of distinct CuZr intermetallics, whereas others suggest that Zr remains in solid solution or segregates into nanoscale clusters [3–7].

Table I: Summary of precipitation phases reported in CuCrZr alloys under different aging conditions.

Reference	Aging Temperature (°C)	Aging Time (h)	Cr-rich Phases	Cu-Zr Phases	Coherency
5	450	1-100	Cr (bbc)	Not detected	Coherent
6	500	4	Cr (bbc)	CuZr	Semi-coherent
7	450-500	1-50	Cr (bbc)	Cu4Zr	Coherent to semi-coherent

These discrepancies in the reported phases can be attributed to variations in nominal alloy composition, solution treatment parameters, and the resolution limits of the characterization techniques employed. Notably, Transmission Electron Microscopy (TEM) has proven crucial in identifying fine, coherent precipitates that fall below the detection threshold of conventional X-ray Diffraction (XRD) [8].

3.2 Influence of Thermomechanical Processing

The mechanical properties of CuCrZr alloys are highly sensitive to the chosen thermomechanical processing route. Pre-aging cold deformation has been demonstrated to accelerate precipitation kinetics and promote a finer, more homogeneous distribution of precipitates, thereby enhancing the alloy's strength [9, 10]. However, severe plastic deformation can induce mechanical anisotropy and compromise the material's ductility, necessitating a careful balance in processing parameters.

3.3. Irradiation Effects and Thermal Stability

A paramount consideration for fusion applications is the alloy's performance under high-energy neutron irradiation. The literature indicates that irradiation generates radiation-induced defects, such as dislocation loops, voids, and gas bubbles, which collectively drive irradiation hardening, embrittlement, and dimensional instability [11, 12]. Conversely, the dispersed Cr and Zr precipitates are believed to serve as effective sinks for mobile point defects, potentially mitigating some of this radiation-induced damage [13]. Concurrently, long-term thermal stability remains a critical design constraint, as reactor components are subjected to elevated temperatures over extended operational lifetimes. Prolonged exposure can trigger overaging and precipitate coarsening, resulting in a gradual loss of strength, while the complete dissolution of precipitates at extreme temperatures (>550°C) can severely degrade the alloy's mechanical integrity

[14].

4. Conclusions

This critical review of the literature on CuCrZr alloys for fusion reactor applications highlights key insights and identifies significant gaps in current knowledge:

1. The precipitation sequence in CuCrZr alloys is complex and highly dependent on processing history. While Cr precipitation is well-established, the precise role of Zr and the exact nature of Cu-Zr intermetallics warrant further elucidation using advanced characterization techniques, such as atom probe tomography (APT).
2. Thermomechanical processing routes that incorporate cold working prior to aging can significantly enhance mechanical properties. However, the optimal parameters (degree of cold work, aging temperature, and duration) exhibit considerable variability across studies, highlighting the need for systematic optimization.
3. Irradiation effects on CuCrZr alloys remain incompletely understood, particularly concerning the long-term stability of precipitates and their interaction with radiation-induced defects. While ion irradiation is frequently used as a surrogate for neutron irradiation, a robust correlation between ion and neutron damage mechanisms must still be established.
4. A critical gap remains regarding comprehensive data on the combined, synergistic effects of thermal aging, mechanical loading, and irradiation, which accurately represent the actual operating conditions within fusion reactors.

Future research should prioritize: (i) advanced *in-situ* characterization of precipitation kinetics; (ii) systematic investigations into the synergistic effects of thermomechanical processing and irradiation; and (iii) the development of robust predictive models for the long-term performance of CuCrZr alloys in next-generation DEMO reactors.

Acknowledgements

The authors are grateful to the Brazilian Agency Capes for the grant received.

References

[1] G. Piatti and D. Boerman, "Hot tensile characteristics and microstructure of a Cu-0.65Cr-0.08Zr alloy for fusion reactor applications," J. Nucl. Mater., vol. 185, pp. 29-38 (1991).
[2] V. Barabash et al., "Materials challenges for ITER – Current status and future activities," J. Nucl. Mater., vol. 367-370, pp. 21-32 (2007).
[3] I. S. Batra, G. K. Dey, U. D. Kulkarni, and S. Banerjee, "Microstructure and properties of a Cu-Cr-Zr alloy," J. Nucl. Mater., vol. 299, pp. 91-100 (2001).
[4] U. Holzwarth and H. Stamm, "Precipitation behaviour of ITER-grade Cu-Cr-Zr alloy after simulating the thermal cycle of hot isostatic pressing," J. Nucl. Mater., vol. 279, pp. 31-45 (2000).
[5] L. Li et al., "Microstructure and properties of Cu-Cr-Zr (Mg) alloys subjected to cryorolling and aging treatment," J. Alloys Compd., vol. 938, p. 168656 (2023).
[6] A. Bodyakova, R. Mishnev, A. Belyakov, and R. Kaibyshev, "Effect of chromium content on precipitation in Cu–Cr–Zr alloys," J. Mater. Sci., vol. 57, pp. 13043-13059 (2022).
[7] D. V. Shangina et al., "Effect of chromium and zirconium content on structure, strength and electrical conductivity of Cu-Cr-Zr alloys after high pressure torsion," Mater. Lett., vol. 199, pp. 46-49 (2017).
[8] L. Sun, N. R. Tao, and K. Lu, "A high strength and high electrical conductivity bulk CuCrZr alloy with nanotwins," Scr. Mater., vol. 99, pp. 73-76 (2015).
[9] L. Gong et al., "Texture evolution and strengthening mechanism of CuCrZr alloys during cold rolling," Vacuum, vol. 221, p. 112908 (2024).
[10] G. Purcek, H. Yanar, O. Saray, I. Karaman, and H. J. Maier, "Effect of precipitation on mechanical

and wear properties of ultrafine-grained Cu–Cr–Zr alloy," Wear, vol. 311, pp. 149-158 (2014).
[11] E. E. Bloom, S. J. Zinkle, and F. W. Wiffen, "Materials to deliver the promise of fusion power - progress and challenges," J. Nucl. Mater., vol. 329-333, pp. 12-19 (2004).
[12] G. S. Was, D. Petti, S. Ukai, and S. Zinkle, "Materials for future nuclear energy systems," J. Nucl. Mater., vol. 527, p. 151837 (2019).
[13] A. Wójcik-Gargula et al., "Evidence of silver impurities in irradiated Cu-based alloys and implications for the long-lived radioactive waste from ITER," Fusion Eng. Des., vol. 224, p. 115575 (2026).
[14] F. Canillas et al., "On the feasibility to obtain CuCrZr alloys with outstanding thermal and mechanical properties by additive manufacturing," J. Nucl. Mater., vol. 601, p. 155304 (2024).