

**The American Ceramic Society**  
**48th International Conference & Exposition  
on Advanced Ceramics and Composites**

**ABSTRACT BOOK**

**January 28–February 2, 2024  
Daytona Beach, Florida**

# Introduction

---

This volume contains abstracts for over 850 presentations during the 48th International Conference & Exposition on Advanced Ceramics & Composites in Daytona Beach, Florida. The abstracts are reproduced as submitted by authors, a format that provides for longer, more detailed descriptions of papers. The American Ceramic Society accepts no responsibility for the content or quality of the abstract content. Abstracts are arranged by day, then by symposium and session title. An Author Index appears at the back of this book. The Meeting Guide contains locations of sessions with times, titles and authors of papers, but not presentation abstracts.

## How to Use the Abstract Book

---

Refer to the Table of Contents to determine page numbers on which specific session abstracts begin. At the beginning of each session are headings that list session title, location and session chair. Starting times for presentations and paper numbers precede each paper title. The Author Index lists each author and the page number on which their abstract can be found.

Copyright © 2024 The American Ceramic Society ([www.ceramics.org](http://www.ceramics.org)). All rights reserved.

### MEETING REGULATIONS

The American Ceramic Society is a nonprofit scientific organization that facilitates the exchange of knowledge meetings and publication of papers for future reference. The Society owns and retains full right to control its publications and its meetings. The Society has an obligation to protect its members and meetings from intrusion by others who may wish to use the meetings for their own private promotion purpose. Literature found not to be in agreement with the Society's goals, in competition with Society services or of an offensive nature will not be displayed anywhere in the vicinity of the meeting. Promotional literature of any kind may not be displayed without the Society's permission and unless the Society provides tables for this purpose. Literature not conforming to this policy or displayed in other than designated areas will be disposed. The Society will not permit unauthorized scheduling of activities during its meeting by any person or group when those activities are conducted at its meeting place in interference with its programs and scheduled activities. The Society does not object to appropriate activities by others during its meetings if it is consulted with regard to time, place, and suitability. Any person or group wishing to conduct any activity at the time and location of the Society meeting must obtain permission from the Executive Director or Director of Meetings, giving full details regarding desired time, place and nature of activity.

**Diversity Statement:** The American Ceramic Society values diverse and inclusive participation within the field of ceramic science and engineering. ACerS strives to promote involvement and access to leadership opportunity regardless of race, ethnicity, gender, religion, age, sexual orientation, nationality, disability, appearance, geographic location, career path or academic level.

Visit the registration desk if you need access to a nursing mother's room or need further assistance. For childcare services, please check with the concierge at individual hotels for a listing of licensed and bonded child care options.

The American Ceramic Society plans to take photographs and video at the conference and reproduce them in educational, news or promotional materials,

whether in print, electronic or other media, including The American Ceramic Society's website. By participating in the conference, you grant The American Ceramic Society the right to use your name and photograph for such purposes. All postings become the property of The American Ceramic Society.

---

During oral sessions conducted during Society meetings, **unauthorized photography, videotaping and audio recording is prohibited**. Failure to comply may result in the removal of the offender from the session or from the remainder of the meeting.

---

**Registration Requirements:** Attendance at any meeting of the Society shall be limited to duly registered persons.

**Disclaimer:** Statements of fact and opinion are the responsibility of the authors alone and do not imply an opinion on the part of the officers, staff or members of The American Ceramic Society. The American Ceramic Society assumes no responsibility for the statements and opinions advanced by the contributors to its publications or by the speakers at its programs; nor does The American Ceramic Society assume any liability for losses or injuries suffered by attendees at its meetings. Registered names and trademarks, etc. used in its publications, even without specific indications thereof, are not to be considered unprotected by the law. Mention of trade names of commercial products does not constitute endorsement or recommendations for use by the publishers, editors or authors.

Final determination of the suitability of any information, procedure or products for use contemplated by any user, and the manner of that use, is the sole responsibility of the user. Expert advice should be obtained at all times when implementation is being considered, particularly where hazardous materials or processes are encountered.

Copyright © 2024. The American Ceramic Society ([www.ceramics.org](http://www.ceramics.org)). All rights reserved.

## Abstracts

conditions, were investigated to produce mechanically stable alumina monoliths with 65 and 80 vol% porosity. The electron microscopy investigation of the pre-sintered alumina monoliths revealed that the size distribution and the shape of the pores could be tailored by controlling the particle size distribution and the shape of the wet pre-expanded microspheres. Highly porous and mechanically stable alumina foams achieved compressive strengths from 3 - 40 MPa. Given the relatively open pore structure, the pore size distribution, the pre-sintered mechanical strength, and the high porosity achieved, the produced alumina foams could potentially be used as support structures for separation, catalytic, and filtration applications. Moreover, the analysis of evolved gases showed the polymer microspheres released nitric oxides (NO<sub>x</sub>), sulfur compounds and CO<sub>x</sub> components while the cellulose microspheres released CO<sub>x</sub> and CH<sub>4</sub> gases suggest a reduction in the evolved harmful components and their low CO<sub>2</sub> impact.

### (ICACC-P082-2024) Zirconia-yttria/lithium-sodium-potassium carbonates ceramic membranes with sodium-potassium carbonate anti-fouling layer for carbon dioxide permeation

T. C. Porfirio<sup>1</sup>; E. N. Muccillo<sup>1</sup>; R. Muccillo<sup>\*1</sup>

1. IPEN, Brazil

The interfaces of porous ZrO<sub>2</sub>:3 mol% Y<sub>2</sub>O<sub>3</sub> (3YSZ), prepared by thermally removing graphite during sintering, were modified by introducing a layer of (Na,K)<sub>2</sub>CO<sub>3</sub> (NKC) before molten (Li,Na,K)<sub>2</sub>CO<sub>3</sub> (LNKC) was impregnated into the pellet pores. X-ray diffraction (XRD), scanning electron microscopy (SEM-EDX), and electrochemical impedance spectroscopy (EIS) were the techniques applied to analyze structural phases, pore content, and carbon dioxide ion conductivity, respectively. EDX analyzes showed that LNKC face-to-face percolation was completed. EIS experiments were conducted at temperatures both below and above the melting point of LNKC for assessing the improvement of carbon dioxide permeation with the introduction of the NKC protective layer, apparently preventing partially 3YSZ-LNKC fouling reaction.

### (ICACC-P083-2024) Application and characterization of a kerosene-fuelled High Velocity Oxy-Fuel (HVOF) Ti<sub>2</sub>AlC coating on thermally stable P91 steel

M. Dujovic<sup>\*1</sup>; A. Maslarevic<sup>2</sup>; G. Bakic<sup>2</sup>; A. Srivastava<sup>1</sup>; M. Radovic<sup>1</sup>

1. Texas A&M University, Materials Science and Engineering (MSEN), USA  
2. Faculty of Mechanical Engineering, University of Belgrade, Department of Materials Technology, Bahamas

A class of ternary layered carbides and nitrides, known as MAX phases, combines some of the best properties of two distinct classes of materials: metals and ceramics. Specifically, MAX phases are stable at high temperatures, resist thermal shock, and some even form stable and protective oxide layers in oxidizing environments. Thus, they are excellent candidates for protective coatings in high-temperature applications. In this context, our focus is on using kerosene-fueled High-Velocity Oxy-Fuel spraying to deposit MAX phases onto P91 steel substrates for use as thermal barrier coatings. The chosen MAX phase for this study is Ti<sub>2</sub>AlC, which offers an outstanding oxidation resistance. Our results indicate that during the spraying procedure, a portion of the MAX phase decomposes, another portion oxidizes, yet more than half maintains the initial and desired stoichiometry. Nevertheless, the resulting coating establishes a stable and robust bond with the steel substrate. In this presentation, we will discuss the detailed analysis concerning the relationship between the process, structure, and performance of the Ti<sub>2</sub>AlC coating on the P91 steel substrate.

### (ICACC-P084-2024) Continuous fiber-reinforced MAX-Phases: Investigation of a Pressure Slip Casting Route for the Production of Al<sub>2</sub>O<sub>3(0)"/Ti<sub>2</sub>AlC-CMCs</sub>

F. Jung<sup>\*1</sup>; L. Aretz<sup>2</sup>; T. Gries<sup>1</sup>; J. Gonzalez-Julian<sup>2</sup>

1. RWTH Aachen University, Institut für Textiltechnik, Germany  
2. Institute of Mineral Engineering of RWTH Aachen University, Germany

MAX phase ceramics show great potential for a new, innovative generation of engineering materials for energy technology due to their excellent mechanical properties in a high-temperature atmosphere. Fiber-reinforcement of MAX phases show great potential to further increase the materials engineering capabilities. However, the mechanisms to introduce continuous fiber-reinforcement into the novel ceramic system are not understood yet. Suitable processes for the production of continuous fiber-reinforced ceramics are currently formulated only by colloidal manufacturing processes. A major challenge of colloidal processes regards the homogeneous impregnation of textile reinforcement structures. However, the formulation of highly filled, fiber-reinforced green bodies decreases with increasing complexity of the molded part design. For this purpose, the production of Al<sub>2</sub>O<sub>3(0)"/Ti<sub>2</sub>AlC-CMC is investigated for the pressure slip casting technology. The innovative composite material is being developed within the publicly funded project ContiMAX (German Research Foundation DFG project No.: 508093957). To this end, the research to be presented is investigating basic mechanisms of MAX phase CMC processing to contribute to the development of future sustainable material systems to replace a large number of metallic high-temperature elements and wear-intensive components.</sub>

### (ICACC-P085-2024) MXene Derived Carbides As Precursors For Ultra High Temperature Ceramics

S. Nemani<sup>\*1</sup>; Y. Im<sup>1</sup>; N. Gilli<sup>2</sup>; B. Sapkota<sup>3</sup>; A. Kumar<sup>4</sup>; A. Vohrees<sup>3</sup>; L. Silvestroni<sup>2</sup>; R. Klie<sup>2</sup>; N. Chawla<sup>4</sup>; B. Anasori<sup>3</sup>

1. Indiana University--Purdue University, Mechanical Engineering, USA  
2. CNR, ISTE, Italy  
3. Indiana University – Purdue University, Mechanical and Energy Engineering, USA  
4. Purdue University, Materials Science, USA  
5. University of Illinois, Physics, USA

Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> MXene is a two-dimensional (2D) refractory carbide which has high solution processability, high aspect ratios, and exhibits one of the highest stiffness (~330 GPa) among solution-processable 2D materials. We have investigated a one-pot, surfactant-free, aqueous mixing method to develop homogeneous ZrB<sub>2</sub>-Ti<sub>3</sub>C<sub>2</sub> MXene green bodies. We present the phase transformation of Ti<sub>3</sub>C<sub>2</sub> MXene to TiC<sub>y</sub> at the grain boundaries upon sintering, role of cationic species on texturing, the interface interactions between the ZrB<sub>2</sub>-TiC<sub>y</sub> grains and their densification mechanisms. A nominal relative density of ~96% is achieved when 0.5 wt.% Ti<sub>3</sub>C<sub>2</sub> MXene is added to ZrB<sub>2</sub> and spark plasma sintered at 1900C with 50 MPa pressure in inert atmospheres. The microstructure evolution, stability, and their effect on micromechanical properties of the resulting UHTCs will be presented and discussed. This study lays the groundwork for 2D MXenes to be used as template precursors for 2D carbides and their implementation as compatible materials for high-temperature applications.

### (ICACC-P086-2024) Thermodynamically Consistent Model of Electrocaloric Effect

M. N. Grinfeld<sup>\*1</sup>

1. U.S. Army Research Laboratory, WMRD, USA

The electrocaloric effect (EE) is a phenomenon in which a material shows a reversible temperature change under an applied electric field. Current state-of-art is presented briefly summarized in the WIKI paper "Electrocaloric effect": "The underlying mechanism of the EE effect is not fully established; in particular, different textbooks give conflicting explanations". One of the main difficulties